

Application No.: 10/091080

Case No.: 57080US002

Amendments to the Claims:

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1. (original) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive slurry comprising
superabrasive particles;
a continuous phase; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater than 500 and an AV of greater than 4.5.
2. (original) The abrasive article of claim 1 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight (Mw) of greater than 1000.
3. (original) The abrasive article of claim 1 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight (Mw) of between about 3000 and about 4000.
4. (original) The abrasive article of claim 3 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having an AV of between about 5 and about 7.5.
5. (original) The abrasive article of claim 1 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight (Mw) of between about 8000 and about 9000.

Application No.: 10/091080

Case No.: 57080US002

6. (original) The abrasive article of claim 5 wherein the abrasive coating is derived from an abrasive slurry comprising a dispersant comprising a polymer having an AV of between about 12 and about 13.
7. (original) The abrasive article of claim 1 wherein the abrasive coating comprises at least about 30% by weight of a superabrasive particle.
8. (original) The abrasive article of claim 7 wherein the abrasive coating comprises between about 30% by weight and about 80% by weight of a superabrasive particle.
9. (original) The abrasive article of claim 1 wherein the abrasive coating is derived from an abrasive slurry further comprising a binder precursor.
10. (original) The abrasive article of claim 9 wherein the abrasive coating comprises a binder.
11. (original) The abrasive article of claim 1 wherein the superabrasive particle is diamond.
12. (original) The abrasive article of claim 11 wherein the diamond has a particle size less than 2 micrometers.
13. (original) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive slurry comprising
superabrasive particles;
a continuous phase; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater than 10,000 and an AV of greater than 1.0.

Application No.: 10/091080

Case No.: 57080US002

14. (original) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20%
by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive
slurry comprising
superabrasive particles;
a continuous phase; and
a dispersant comprising a polymer having a molecular weight (Mw) of greater
than 100,000 and an AV of greater than 0.
15. (original) The abrasive article of claim 14 wherein the abrasive coating is derived from
an abrasive slurry comprising a dispersant comprising a polymer having a molecular weight
(Mw) of greater than 150,000.
16. (original) An abrasive article comprising
a backing having a major surface; and
an abrasive coating on the major surface of the backing comprising at least 20%
by weight of a superabrasive particle, wherein the abrasive coating is derived from an abrasive
slurry comprising
superabrasive particles;
a continuous phase; and
a dispersant comprising a polymer having a molecular weight (Mw) of
greater than 500 and a measurable total Amine Value.
17. (original) A method of manufacturing an abrasive article comprising
coating an abrasive slurry comprising superabrasive particles, a continuous phase
and a dispersant comprising a polymer having an average molecular weight (Mw) of greater than
500 and an AV of greater than 4.5 onto a backing, wherein the superabrasive particles comprise
at least 20% dry weight of all solids in the slurry; and

Application No.: 10/091080

Case No.: 57080US002

solidifying the abrasive slurry.

18. (original) The method of claim 17 wherein the abrasive slurry is cured.
19. (previously presented) An abrasive article comprising
 - a backing having a major surface; and
 - an abrasive coating on the major surface of the backing comprising at least 20% by weight of a superabrasive particle, wherein the abrasive coating comprises
 - superabrasive particles;
 - a continuous phase; and
 - a dispersant comprising a polymer having a molecular weight (Mw) of greater than 500 and an AV of greater than 4.5.